

Würzburg Germany


Via Paolo Paoletti 10, 51037 Montale (PT) Italy - EUROPE




ECOFELT PES-SB 800

**NONWOVEN NEEDLED FABRIC
PRODUCED WITH PES (POLYESTER) FIBER, WITHOUT CHEMICAL TREATMENTS**


Intended functions:




Separazione / Separation /
Séparation / Trennung




Filtrazione / Filtering /
Filtration / Filterung



Drenaggio / Drainage /
Drainage / Dränung



Protezione / Protection /
Schutzfunktion / Protection



Rinforzo / Reinforcement /
Renforcement / Verstärkung

FEATURES	NORM	U.M	AVERAGE	TOLLERANCE
AERIC MASS	UNI EN ISO 9864	gr/mq	800	+/- 10%
THICKNESS (2kPa)	UNI EN ISO 9863	mm.	5,12	-1,536
LONGITUDINAL TRACT. RESISTANCE	EN ISO 10319	kN/m	8	-2,4
TRASNVERSAL TRACT. RESISTANCE	EN ISO 10319	kN/m	8,8	-2,64
LONGITUDINAL ELONGATION	EN ISO 10319	%	50	-20%
TRANSVERSAL ELONGATION	EN ISO 10319	%	50	-20%
ENERGY ABSORPTION INDEX	EN ISO 10318	kJ/m ²	3,4	-1,536
STATIC PUNCHING	EN ISO 12236	kN	1,47	-0,44
DYNAMIC PUNCHING	UNI EN ISO 13433	mm.	nc	+30%
OPENING SIZE	EN ISO 12956	um.	40	+/- 30%
WATER PERMEABILITY PERP. ON PLANE	EN ISO 11058	m/s	0,0195	+/- 30%
DRAINING CAPACITY IN PLANE (20kPa)	EN ISO 12958	m ² /s	1,90E-06	+/- 30%
DURABILITY	UNI EN 12224	Predicting durability of minimum 5 years in natural soils with 4 <pH <9 and soil temperature <25 °. Be covered within 2 weeks from installation.		

EN 13249 Strade / Roads Strassen / Routes	EN 13250 Ferrovie / Railways Schienenbau / Rail	EN 13251 Fondazioni / Foundations Fundamenten / Fondations	EN 13252 Drenaggio / Drainage System Draensystem / Drainage	EN 13253 AntiErosione / Erosion Control Erosionsschutz / Erosion
EN 13254 Bacini / Dams Staudaemme / Barrages	EN 13255 Canali / Canals Kaenalenbau / Canaux	EN 13256 Tunnel / Tunnels Tunnelbau / Tunnel	EN 13257 Rifiuti Solidi / Solid Waste Deponiebau / Dechets Solid	EN 13265 Rifiuti Liquidi / Liquio vaste Fluessige Deponieabfall / Dechets Liquides

The above mentioned values have been obtained in Ecofibre SRL laboratory and in accredited outer Laboratories.

The values are real and correct according to our knowledge.

Roll lenght tolerance +/-2%, width tolerance +/-3cm

Montale 05-mar-18

Quality Control Manager
ECOFIBRE s.r.l.