

Würzburg Germany


Via Paolo Paoletti 10, 51037 Montale (PT) Italy - EUROPE




ECOFELT PP-FC/AG 350

NONWOVEN NEEDLED FABRIC
PRODUCED WITH PP (POLYPROPYLENE) HT FIBER, WITHOUT CHEMICAL TREATMENTS, UV RAYS STABILIZED

Funzioni / Function / Anwendungen / Function




Separazione / Separation /
Séparation / Trennung




Filtrazione / Filtering /
Filtration / Filterung



Drenaggio / Drainage /
Drainage / Dränung



Protezione / Protection /
Schutzfunktion/ Protection/



Rinforzo / Reinforcement /
Renforcement / Verstärkung

FEATURES	NORM	U.M	AVERAGE	TOLERANCE
AERIC MASS	UNI EN ISO 9864	g/m ²	350	+/- 10%
THICKNESS (2kPa)	UNI EN ISO 9863	mm.	2,24	-0,672
TENSILE STRENGTH RESISTANCE MD	EN ISO 10319	kN/m	27,3	-4,095
TENSILE STRENGTH RESISTANCE CMD	EN ISO 10319	kN/m	28	-4,2
ELONGATION MD	EN ISO 10319	%	>50	-
ELONGATION CMD	EN ISO 10319	%	>50	-
ENERGY ABSORPTION INDEX	EN ISO 10318	kJ/m ²	11,1	-0,144
STATIC PUNCHING	EN ISO 12236	kN	4,5	-0,9
DYNAMIC PUNCHING	UNI EN ISO 13433	mm.	7	2,1
OPENING SIZE	EN ISO 12956	um.	80	+/- 30%
WATER PERMEABILITY PERP. ON PLANE	EN ISO 11058	m/s	0,057	+/- 30%
DRAINING CAPACITY IN PLANE (20kPa)	EN ISO 12958	m ² /s	4,40E-06	+/- 30%
DURABILITY	EN ISO 12224	Be covered within one month. Predicting durability of minimum 50 years in natural soils with 4 <pH <9 and soil temperature <25 °.		

<p><input checked="" type="checkbox"/> EN 13249 Strade / Roads Strassen / Routes</p>	<p><input checked="" type="checkbox"/> EN 13250 Ferrovie / Railways Schienenbau / Rail</p>	<p><input checked="" type="checkbox"/> EN 13251 Fondazioni / Foundations Fundamenten / Fondations</p>	<p><input checked="" type="checkbox"/> EN 13252 Drenaggio / Drainage System Draensystem / Drainage</p>	<p><input checked="" type="checkbox"/> EN 13253 AntiErosione / Erosion Control Erosionsschutz / Erosion</p>
<p><input checked="" type="checkbox"/> EN 13254 Bacini / Dams Staudaemme / Barrages</p>	<p><input checked="" type="checkbox"/> EN 13255 Canali / Canals Kaenalnenbau / Canaux</p>	<p><input checked="" type="checkbox"/> EN 13256 Tunnel / Tunnels Tunnelbau / Tunnel</p>	<p><input checked="" type="checkbox"/> EN 13265 Rifiuti Liquidi / Liquid Waste Deponiebau / Dechets Liquides</p>	

The above mentioned values have been obtained in Ecofibre SRL laboratory and in accredited outer Laboratories.

The values are real and correct according to our knowledge. The values can be updated in any time without advise.

Roll lenght tolerance +/-2%, width tolerance +/-3cm

Quality Control Manager
ECOFIBRE s.r.l.